

DIRECT-TO-FILM

APPLICATION INSTRUCTIONS

APPLICATION


INSTRUCTIONS:



12-15 SECONDS



300°F / 145°C



MEDIUM



COOL

ALWAYS TEST THE CORNER BEFORE ATTEMPTING TO PEEL
LET COOL LONGER IF NEEDED BEFORE PRESSING AGAIN



2ND PRESS 5 SECONDS

NOTE: Yellowing of the adhesive or waffle texture on the carrier is possible and normal. This will not affect heat application.